

SPECIFICATION

TITLE OF THE INVENTION

MAGNETORESISTIVE SENSOR INCLUDING MAGNETIC DOMAIN
CONTROL LAYERS HAVING HIGH ELECTRIC RESISTIVITY,
5 MAGNETIC HEAD AND MAGNETIC DISK APPARATUS

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to a
10 magnetoresistive sensor including magnetic domain
control layers for the magnetoresistive sensor for
reading back magnetically recorded information, a
magnetic head, and a magnetic disk apparatus. More
specifically, it relates to a magnetoresistive sensor
15 having excellent reproducing resolution, a magnetic
head using the same, and a magnetic disk apparatus.

Description of the Related Art

The recording density in a magnetic disk
apparatus has been improved significantly, and the
20 demand that the performance of the magnetic read/write
heads thereof be enhanced is increased in regard to
both characteristics of read and write.

Regarding the read head sensor, it is necessary
to improve the techniques concerning three points: (1)
25 improvement of a technique for making the efficiency
higher, (2) improvement of a technique for making the
track width smaller, and (3) a technique for making the
gap between the write magnetic shields smaller.

With respect to (1), making the efficiency higher has been advanced by developing an MR head utilizing a magnetoresistive effect. At a low recording density of several giga bits per square inch (Gb/in²), anisotropic magnetoresistive effect (AMR) is used to convert the magnetic signal on recording media to an electric signal. At a high recording density exceeding this, a higher efficient giant magnetoresistive effect (GMR) is used to respond to this high recording density. However, when making the efficiency much higher is advanced, the structure must be changed to the perpendicular magnetic recording structure in relation to the read element, which makes the most of GMR (CPP - GMR) or a tunnel magnetoresistive effect (TMR) of a system for flowing a sensing current perpendicular to the plane.

As a known example of a magnetic head employing GMR, Japanese Patent Publication No. Hei 8(96)-21166 (Japanese Un-examined Patent Publication No. Hei 4(92)-358310) describes the structure called a spin valve.

This comprises a pinned layer consisting of a magnetic material in which a anti-ferromagnetic layer pins magnetization in the specific direction, and a free layer consisting of a non-magnetic thin film laminated on the pinned layer and a magnetic layer laminated through the non-magnetic thin film, so as to change electric resistance at a relative angle of magnetization of the pinned layer and the free layer.

With respect to (2), the track width is made

smaller to improve the track density. It is generally thought that the read track width is determined by the distance between electrodes flowing a sensing current for sensing changed resistance. The read sensor has a high loss of S/N when Barkhausen noise is caused, and it is necessary to control this. The Barkhausen noise is caused together with microscopic domain wall movement, and there must be arranged magnetic domain control layers so as to provide the read sensor singly in the form of a magnetic domain. The magnetic domain control layers are often arranged on opposite sides of the sensor layer portion of the read sensor, viewed from the media-opposed surface side. The magnetic domain control layer is generally a hard magnetic metal material layer formed on a suitable metal underlayer, and an insulating oxide layer is required for the contact surface of the same with the magnetoresistive sensor layer, the top surface of the lower shield, and the contact surface of the same with the upper shield. The magnetic domain control layer provides a magnetic field for the magnetoresistive sensor layer, so that the anisotropic magnetic field is increased effectively and the exterior magnetic efficiency is reduced greatly. For this reason, Japanese Un-examined Patent Publication No. Hei 9(97)-282618 describes the structure in which the gap between the electrodes is smaller, than that between the magnetic domain control layers, and a sensor region having an efficiency

effective for the exterior magnetic field is used for sensing a signal.

With respect to (3) the technique for making the read gap smaller, that is, for making the gap between the read magnetic shields smaller, there has been studied improvement of linear recording density by modifying resolution. Generally, the shield layers are arranged at the upper and lower sides so as to interpose the magnetoresistive sensor layer, and a gap layer made of an insulating material is disposed between the shield layer and the magnetoresistive sensor layer so as to prevent a sensing current from being leaked to the shield. When the gap between the read magnetic shields is smaller, the thickness of the gap layer is reduced. Thus, the thickness dependence as the characteristic of the insulating layer or the presence of pinhole cannot maintain the insulating properties, so that an electric current for sensing a signal (sensing current) is leaked to the magnetic shield to reduce read output. This loss is called a shunting loss.

As a method of solving this, Japanese Un-examined Patent Publication No. Hei 5(93)-266437 describes the structure in which an insulating magnetic layer is arranged on the surface of the magnetoresistive sensor layer side of at least one of the magnetic shields.

The read element is difficult to provide a sufficient recording magnetic field in a conventional

in-plane magnetic recording system. Further, CPP
(Current Perpendicular to the Plane) - GMR or TMR as a
high efficient magnetoresistive sensor is a
magnetoresistive sensor utilizing a structure flowing a
5 sensing current perpendicular to the plane. Thus, a
future structure of the read element is thought to be
of the CPP system employing a sensing current. However,
employing such a structure, when the area of the
magnetoresistive sensor layer is reduced, there arises
10 a new problem that the conventional magnetic domain
control layer is difficult to ensure the insulating
properties of the magnetic domain control layer. In
other words, the conventional magnetic domain control
layer is arranged on the lower magnetic shield by
15 employing a laminating structure of insulating
layer/(metal underlayer)/hard magnetic metal material
layer/insulating layer, and then is in contact with
opposite ends of the magnetoresistive sensor layer. The
magnetoresistive sensor layer is made thinner and
20 finer; there are imposed three problems: (1) the
throwing power of the lower insulating layer is
insufficient so as to shunt the sensing current flowing
to the magnetoresistive sensor layer to the magnetic
domain control layer, resulting in reduction of output,
25 (2) the thick lower insulating layer is adhered so as
to increase the gap between the magnetoresistive sensor
layer and the magnetic domain control layer, thereby
making the magnetic domain control different from the

design, and (3) in consideration of the thickness
maintaining the pressure resistance of the insulating
layer, the magnetic layer thickness of the magnetic
domain control layer is reduced relatively, so as not
5 to ensure a predetermined susceptibility, thereby
making it difficult to design the magnetic domain
control. Further, when employing the yoke structure or
the flux guide structure of the TMR element, these must
be magnetic domain controlled. Simply, there is
10 employed means for laminating a plurality of the above-
mentioned magnetic domain control layer. This will
involve a very difficult problem in process.

SUMMARY OF THE INVENTION

15 An object of the present invention is to provide
a magnetoresistive sensor having, in particular,
excellent reproducing resolution, in magnetic read and
write, a magnetic head using the same, and a magnetic
disk apparatus, and, for that, to provide magnetic
20 domain control layers having high electric resistivity
suitable for improving the reproducing resolution of
the magnetoresistive sensor.

In order to achieve the foregoing objects, the
present invention solves the above-mentioned problems
25 with respect to the magnetic domain control layer by
the following means, and provides a magnetoresistive
sensor having excellent reproducing resolution, a
magnetic head using the same, and a magnetic disk

apparatus.

Conventionally, the magnetic domain control layer is arranged on the lower magnetic shield by employing a multi-layered structure of insulating layer/(metal underlayer)/hard magnetic metal material layer/insulating layer. In the present invention, there is used means wherein the magnetic domain control layer comprises a single layer made of a hard magnetic material having high electric resistivity, thereby directly performing magnetic domain control. According to this method, the insulating layers arranged at the upper and lower sides of the magnetic layer can be omitted. Thus, when the magnetoresistive sensor layer is made thinner, a loss of the susceptibility due to the thickness of the insulating layer can be reduced, so as to lower the shunting loss of an electric current. In addition, since the magnetic domain control layer is in direct contact with the magnetoresistive sensor layer, the loss of the magnetic field of the magnetic domain control can be minimized.

As a hard magnetic material having high electric resistivity with such characteristics, there are (1) a magnetic oxide having a spinel lattice, and (2) a granular magnetic material made of a hard magnetic metal material and a non-magnetic insulating material. With respect to (1), there is γ -Fe₂O₃ or the like. When a γ -Fe₂O₃ (004) layer grows, the residual magnetization is relatively large, the coercivity is

high, and the specific resistance is high and 10^5 to $10^6 \Omega \text{cm}$. Thus, this is adaptable to the above-mentioned single magnetic domain control layer. As for such a system, there is also $\gamma\text{-(FeCo)}_2\text{O}_4$.

5 However, in order to exhibit the magnetic characteristic by making the spinel lattice thinner, it is generally necessary to manufacture the layer at a very high substrate temperature (above 500°C). When the layer is manufactured in a practical temperature range below 300°C using a sputtering method, it tends to be an amorphous layer. As means of solving this, there is envisaged a method of inserting one high orientation thin oxide film or one single crystal thin film, with an NaCl structure, under the spinel lattice magnetic layer, so as to form thereon the above-mentioned magnetic domain control layer having high electric resistivity, and this is used as means.

10 Examples of the underlayer material for use in this method include CoO (200), MgO (200), NiO (200), EuO (200), FeO (200) and ZnO (001). These materials can be relatively easily grown at room temperature by means of the sputtering method. When a spinel type compound $\gamma\text{-Fe}_2\text{O}_3$ is grown on this plane, it is found that the $\gamma\text{-Fe}_2\text{O}_3$ (400) plane can be manufactured on these oxides in a relatively low temperature range below 300°C . These thin oxide films can exhibit a function as the underlayer even in the thickness range of 1 nm to 5 nm. These underlayers are electrically an

insulator to insulating semiconductor. Basically, they can eliminate shunting from the magnetoresistive sensor layer to the magnetic domain control layer.

In the granular magnetic material made of a hard magnetic metal material and a non-magnetic insulating material, the multi-layer laminated is formed using the mixed sputtering method or the sputtering method, so that a hard magnetic material in granular form is formed in the non-magnetic insulating material. At this time, when the granular volume is smaller than the critical volume (granular volume V in which thermal energy kT is larger than magnetic energy $MV + KV$), the material becomes magnetically paramagnetic, or weak soft magnetic. However, when the granular particle is larger than the critical volume and the granular shape is changed anisotropically for pinning by the insulator, it can become magnetically hard. The granular magnetic material of the present invention is a material in which the hard magnetic metal material is enclosed by the non-magnetic insulating material, and the granular volume is larger than the critical volume. When the above-mentioned conditions are met, the granular shape is optional.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a diagram showing the sectional structure of the media-opposed surface side of the magnetoresistive sensor of Example 1 of the present

invention and the position of a magnetic domain control layer;

FIG. 2 is a cross-sectional view of the depth direction of the magnetoresistive sensor of Example 1 of the present invention;

FIG. 3 is a cross-sectional view of the media-opposed surface side of Example 1 (3) of the present invention showing the position relation between the magnetic domain control layer having high electric resistivity and the magnetoresistive sensor layer;

FIG. 4 is a cross-sectional view of the media-opposed surface side of Example 1 (2) of the present invention showing the position relation between the magnetic domain control layer having high electric resistivity and the magnetoresistive sensor layer;

FIG. 5 is a cross-sectional view of the media-opposed surface side of Example 1 (1) of the present invention showing the position relation between the magnetic domain control layer having high electric resistivity and the magnetoresistive sensor layer;

FIG. 6 is a cross-sectional view of the media-opposed surface side of Example 1 (4) of the present invention showing the position relation between the magnetic domain control layer having high electric resistivity and the magnetoresistive sensor layer;

FIG. 7 is a cross-sectional view of the media-opposed surface side of Example 4 of the present invention showing the position relation between the

magnetic domain control layer having high electric resistivity and the magnetoresistive sensor layer;

5 FIG. 8 is a diagram showing the sectional structure of the media-opposed surface side of the magnetoresistive sensor of Example 5 of the present invention and the position of the magnetic domain control layer;

10 FIG. 9 is a cross-sectional view of the depth direction of the magnetoresistive sensor of Example 5 of the present invention;

15 FIG. 10 is a three-dimensional block diagram showing the structure of the exposed type magnetoresistive sensor of Examples 1 and 5 of the present invention;

20 FIG. 11 is a block diagram schematically showing one example of the yoke structure shown in Example 5 of the present invention and the position of the magnetic domain control layers of the present invention to magnetic domain-control this;

25 FIG. 12 is one example of the position of the magnetic domain control layers of the yoke structure shown in Example 5 of the present invention;

 FIG. 13 is one example of the position of the magnetic domain control layers of the yoke structure shown in Example 5 of the present invention;

 FIG. 14 is a block diagram schematically showing one example of the flux guide type yoke structure shown in Example 5 of the present invention and one example

of the position of the magnetic domain control layers of the present invention to magnetic domain-control this;

5 FIG. 15 is a diagram showing one example of the shape of the flux guide type yoke of Example 5 of the present invention, and one example of the position relation between the same and the magnetoresistive sensor;

10 FIG. 16 is a diagram showing one example of the shape of the flux guide type yoke of Example 5 of the present invention, and one example of the position relation between the same and the magnetoresistive sensor layer;

15 FIG. 17 is one example of the position of the magnetic domain control layers of the yoke structure shown in Example 5 of the present invention;

FIG. 18 is one example of the position of the magnetic domain control layers of the yoke structure shown in Example 5 of the present invention;

20 FIG. 19 is a schematic diagram of the structure and operation of a magnetic disk apparatus of Example 6 of the present invention;

25 FIG. 20 is a side view of one example of the structure of MRAM using the magnetoresistive sensor layer provided with the magnetic domain control layers having high electric resistivity of the present invention;

FIG. 21 is a diagram of FIG. 20 viewed

perpendicular to the substrate surface (representing state "1"); and

FIG. 22 is a diagram in which the direction of an electric current flowing through the conductive line is shifted 90 degrees from that of FIG. 21 (representing state "0").

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Embodiments of the present invention will be described based on the examples with reference to the drawings.

(Example 1)

FIGS. 1 and 2 are diagrams showing the structure of a magnetoresistive sensor as one embodiment according to the present invention viewed from the media-opposed surface and section of the plane perpendicular to the depth direction, respectively. Arrow 110 in the drawing denotes the depth direction.

On a substrate 101 is formed a base insulating layer 102, made of, for example, alumina. After subjected to precision polishing by means of chemimechanical polishing (CMP), a lower magnetic shield layer 103 is formed thereon. This is made of Ni81Fe19 having a thickness of 2 μ m manufactured by, for example, the sputtering method, the ion beam sputtering method, or the plating method. A resist mask is patterned in a predetermined size in this layer, and other portions thereof are subjected to ion milling to

strip off the resist. Al₂O₃ is grown thereon to fill in portions 104 removed by ion milling. After this is subjected to CMP, an electrode layer made of Cu or Ru (not shown) is grown by 20 nm, so as to form a drawing electrode layer 111 in a portion away from the sensor portion. This is, for example, a layer made of Ta, Au and Ta.

A lift-off pattern is formed in a region on the previous electrode layer consisting of a magnetoresistive sensor layer, so as to form thereon a layer having a thickness of 150 nm made of a mixture of Al₂O₃ and SiO₂. This may be a single phase layer made of Al₂O₃ or SiO₂. After lifting this off, a magnetoresistive sensor layer 105 is formed. In the magnetoresistive sensor layer, there are studied as the examples two types of using GMR and of using TMR. An electric current for sensing a signal (sensing current) is flowed perpendicular to the plane of these magnetoresistive sensor layers (Current Perpendicular to the Plane: CPP).

A GMR layer comprises, for example, from the lower side, a Co₄₈Mn₅₂ anti-ferromagnetic layer of 12 nm, a pinned layer consisting of Co of 1 nm, Ru of 0.8 nm and Co of 2 nm, a free layer consisting of Cu of 2 nm, Co of 0.5 nm and Ni₈₁Fe₁₉ of 2.5 nm, and Ta of 3 nm. With respect to the anti-ferromagnetic layer, in the case of using a regular anti-ferromagnetic layer of a PtMn system, anneal is required in order to exhibit the

exchange bonding between the pinned layer and the anti-ferromagnetic layer. The magnetic field of the pinned layer is directed in the in-plane direction orthogonal to the depth.

5 On the other hand, a TMR layer comprises, for example, from the lower side, a free layer consisting of Ta of 5 nm, NiFe of 3 nm and a CoFe layer of 2 nm, a barrier layer consisting of Al₂O₃ of 2 nm, a pinned layer consisting of CoFe of 2 nm, Ru of 1 nm and CoFe of 1 nm, a anti-ferromagnetic layer consisting of MnIr of 10 nm, Ta of 3 nm, and NiFe of 5 nm.

10 After forming the magnetoresistive sensor layer 105, a lift-off material is formed in the position as an active region (on the layer served both as the lower shield and electrode). Then, the magnetoresistive sensor layer is etched, for example, by the ion milling method. After etching, magnetic domain control layers 106 are formed so as to remove the lift-off mask. Thereafter, a pattern in the depth direction of the magnetoresistive sensor layer 105 is formed in the magnetic domain control layers 106, and then, the portion therearound is removed by the ion milling. A mixed layer of Al₂O₃ and SiO₂ having a thickness of 150 nm is formed thereon as a protective insulating layer 107 to define an upper shield layer 112.

25 A write element having a magnetic core laminated through a recording gap is formed on the magnetoresistive sensor to define a magnetic head of

the magnetic disk apparatus.

By means of a method represented by the above-mentioned manufacture method, the magnetoresistive sensor of the present invention and the magnetic head using the same are manufactured. In this, the magnetic domain control layer 106 has a required characteristic different from the case of flowing an electric current in the plane. In the magnetic domain control layer, there have been studied the magnetic domain control layer itself is: (1) a layer made by laminating, from the lower portion, an insulating layer Al₂O₃ - SiO₂ layer of 220 nm, a Cr underlayer of 5 nm, a magnetic layer CoCrPt of 25 nm, and an insulating protective Al₂O₃ - SiO₂ layer of 220 nm on the top, (2) a layer made by laminating, as the magnetic layer, a CoO underlayer of 5 nm, and a γ -Fe₂O₃ layer of 50 nm, (3) a layer made by laminating, as the magnetic layer, a γ -Fe₂O₃ layer of 50 nm, and (4) a layer by alternately laminating CoCrPt of 1.5 nm and SiO₂ of 1.1 nm (60 nm thick).

In the method (1), there is shown a conventional magnetic domain control layer as shown in the schematic structure of FIG. 5, as a comparative example. When the conventional magnetic domain control layer is applied as-is, the gap between the shields Gs not less than 70 nm makes it possible to manufacture magnetic domain control layers 501, 502 and 503. However, the following points in formation of the junction of the ends of the

magnetoresistive sensor layer are important in order to maintain insulation of the CoCrPt (502) from the lower portion Al2O3 (501).

One of the points is that, in order to maintain insulation, the ends of the magnetoresistive sensor layer 105 must be completely coated by the Al2O3 layer 501, the hard metal magnetic CoCrPt (502) must be grown thereon, and the Al2O3 layer 503 grown thereon must completely coat the CoCrPt layer. For this reason, the sputtering apparatus forming the layer needs to have a characteristic such that the Al2O3 is inserted into the lift-off pattern in the plane, and CoCrPt is not inserted deeply therein, and to ensure such manufacture conditions. Further, for manufacture, the lift-off pattern must be formed, and when the size of the sensor is reduced (not more than 1 μm), the formation thereof is difficult. The insulating layer having a thickness less than 20 nm cannot have sufficient insulation properties, and when the layer is thick in order to maintain the sufficient insulation properties, the gap between the end of the magnetoresistive sensor layer 105 and the CoCrPt layer as the magnetic domain control layer is larger, so that the magnetic domain control force is weak, thereby making magnetic domain control impossible. For this reason, when the gap between the shields is not more than 70 nm in order to make the resolution of the read head high, the method (1) is difficult to use.

The method (2) is one embodiment of the present invention shown in FIG. 4. First, a lower shield 302 is formed on an appropriately treated substrate 301, and the region in contact with opposite ends of the magnetoresistive sensor layer 105 thereon is formed with a CoO underlayers 304. CoO (002) is grown in the CoO underlayer, and γ -Fe₂O₃ (65 nm) is formed thereon, so as to manufacture a magnetic domain control layer 303. γ -Fe₂O₃ has a (004) orientation plane by the effect of the underlayer. This is the same for Co- γ -Fe₂O₃ as other ferrite.

This layer has a specific resistance not less than several $10\Omega\text{cm}$ in the layer state. In this case, the layer requires no lift-off pattern, and can be manufactured by the usual resist pattern. The magnetoresistive sensor layer may be in contact with the magnetic domain control layer, or the magnetic domain control layer may be lifted on the magnetoresistive sensor layer. According to this method, the magnetic domain control layer has electric resistivity much higher than the magnetoresistive sensor layer. A signal sensing current flows only through the magnetoresistive sensor layer, so as to eliminate a loss of the signal intensity due to shunting to the magnetic domain control layer.

Even when the gap between the shields is smaller, the insulating protective layer of conventional type is unnecessary. According to this, it is possible to

reduce the total thickness of the magnetic domain control layer causing an equivalent susceptibility. The susceptibility is an amount to determine the thickness of the magnetic domain control layer by multiplying the magnetization of the free layer of the magnetoresistive sensor layer by the thickness thereof. In the case of the magnetic domain control layer, multiplication of the residual magnetization by the thickness is equivalent to this. γ -Fe₂O₃ or Co- γ -Fe₂O₃ in this study has a high specific resistance of 10^5 to $10^6 \Omega \text{cm}$, a coercivity of about 1.3 to 5.0 kOe, a residual magnetization of 1.2 to 3.5 kG, and a saturated magnetization of 3.5 to 4.2 kG. These values are smaller than those of CoCrPt (having a coercivity of about 1.0 to 3.0 kOe, a residual magnetization of 4 to 9 kG, and a saturated magnetization of 6.5 to 12.0 kG). In consideration of the protective insulating layer, it is effective for the magnetic domain control when the gap between the shields is small. As the layer formation process, the conventional four layers (Al₂O₃/Cr/CoCrPt/Al₂O₃) can be reduced to two layers, so as to make the operation efficient.

In the method (3) as another example of the present invention, FIG. 3 shows a basic construction. This is the same as the method (2) except that the oxide underlayer 304 of the magnetic domain control layer is absent. In view of the manufacture method, the point of directly forming γ -Fe₂O₃ is different. In

this case, the substrate temperature is raised to 300 to 500 °C, and then, the layer is formed by the high vacuum layer forming apparatus having a maximum degree of vacuum of 10^{-11} Torr, or the top surface of the lower shield exposed is irradiated with an oxygen ion using an ECR ion source to oxidize the surface, so that γ -Fe₂O₃ can be precedably grown. In this case, the same effect as in the method (2) is found to be given.

The method (4) as another example of the present invention has the structure of FIG. 6. A magnetic domain control layer 601 in this case is a layer by alternately laminating CoCrPt of 1.5 nm and SiO₂ of 1.1 nm. The thickness ratio of CoCrPt/SiO₂ is between 2 : 1 and 1 : 2, CoCrPt has a layer thickness of 0.5 to 2 nm, a specific resistance not less than 10 mΩcm, a coercivity not more than about 1.0 kOe, and a residual magnetization of 2 to 4 kG, so as to give the same effect as described above. However, in this case, it is more effective that Al₂O₃ not less than 10 nm is inserted for the underlayer.

In the methods (2) to (4) of this example, even when the gap between the read shields (gap distance) is not more than 70 nm, the read characteristic is not found to be deteriorated due to the conduction of the magnetoresistive sensor layer and the magnetic domain control layer.

(Example 2)

The magnetoresistive sensor in Example (1)

described above has the structure by lamination from the lower portion. The structure in which the upper and lower portions are reversed can also give the same effect.

5 (Example 3)

10 In Example (1) described above, in formation of the magnetic domain control layer using a spinel type oxide such as γ -Fe₂O₃, on the underlayer 304 of the magnetic domain control layer 303, is formed, in place of the CoO layer, an oxide layer having a crystal structure of NaCl type such as Mg (200), NiO (200), EuO (200), FeO (200) or ZnO (200) as well as a (200) plane. Then, the spinel ferrite formed thereon can be crystallized at low temperature. As a method of forming this layer, there is a method of manufacturing these layers by the sputtering method, the ion beam sputtering method or the cluster ion beam method. As a method other than this, on the lower shield 302 a layer of Co, Mg, Ni, Eu, Fe or Zn is formed in a thickness of 1-5 nm. This layer is exposed to oxygen in vacuum, is irradiated with oxygen using ECR plasma, or is exposed to low-pressure oxygen by heating the substrate (100 to 250 °C) so as to form an oxide layer, thereby forming a spinel ferrite thereon. This method can give equivalent results.

25 As a spinel type oxide formed on the oxide underlayer 304, there are γ -Fe₂O₃ and Co- γ -Fe₂O₃. The latter is thought to be a solid solution of γ -Fe₂O₃

and CoFe_2O_3 , and is represented by the chemical formula $(\text{Co}(\gamma)\text{Fe}(8-2\gamma)/3)\text{O}_4(\gamma-\text{Fe}_2\text{O}_3)$. The ratio of Co is varied to change the coercivity. As compared with the case that these are formed on a glass substrate, a high
5 coercivity increased 1.5 to 2 times is exhibited in the same thickness as that of these formed on the oxide underlayer, and when the Co/Fe ratio is 0.08, a coercivity of 2.6 kOe in 10 nm.

(Example 4)

10 Before forming the magnetic domain control layer of Example 1 (1), as shown in FIG. 7, portions 701 are formed with MnZn ferrite as a soft magnetic layer having high electric resistivity, an insulator and a metal magnetic material are alternately laminated, or
15 there is formed a granular layer in which these are sputtered at the same time into a mixed state, for example, a layer by laminating, by 25 number of layers, $\text{Co}_{90}\text{Fe}_{10}$ layers having a thickness of 1.4 nm and Al_2O_3 layers having a thickness of 1.0 nm. Thereafter, the
20 outside of the layer is removed by the ion milling in the position several mm away from the outer peripheral portion of the magnetoresistive sensor layer, and then metal magnetic layers such as CoCrPt as represented by 502 are formed in the removed portions. This structure
25 has no shunting since the metal magnetic domain control layers 502 are not in direct contact with the magnetoresistive sensor layer. However, since a layer with soft magnetic properties is disposed therebetween,

the magnetic field of the magnetic domain control is effectively applied to the magnetoresistive sensor layer.

(Example 5)

5 In the magnetoresistive sensor with the magnetoresistive sensor layer is exposed, according to a three-dimensional schematic diagram exploding the structure of the magnetoresistive sensor, as shown in FIG. 10, the magnetic domain control layers 106 are
10 arranged on opposite ends of the magnetoresistive sensor layer 105, and the magnetic shields 103 and 109 are disposed at the upper and lower sides thereof. In the present invention described in the above examples, the layer 106 is a material having high electric
15 resistivity. There is a magnetoresistive sensor of another structure, that is, a magnetoresistive sensor provided with a yoke structure as the write sensor. FIG. 11 is a three-dimensional diagram schematically showing a representative yoke structure and the magnetic domain
20 control layer. In this structure, a magnetoresistive sensor layer 1105 is not exposed from the surface opposite the media. In the gap between a lower magnetic shield 1103 and an upper magnetic shield 1107, made of Ni81Fe19, are arranged yoke layers made of a similar
25 soft magnetic material. The properties of this structure described below are observed. In FIG. 11, the yoke layers in C ring form consist of an upper yoke 1106 joined to a lower yoke 1102. Other than this, the

lower yoke is reduced on the end thereof, or has a thick film, or the yoke is discontinuous under the magnetoresistive sensor layer. In the diagram, a magnetic domain control layer 1101 is shown. The magnetic domain control layer having high electric resistivity shown in Example 1 of the present invention is used as the layer. This magnetic domain-controls at least the lower yoke and the magnetoresistive sensor layer and has no shunting in the periphery. The magnetic domain control layer has a type for magnetic domain-controlling the upper and lower yoke layers and the magnetoresistive sensor layer at the same time, and a type for magnetic domain-controlling each. In either structure, it is found that the good magnetic domain control is possible without shunting.

The above-mentioned FIG. 11 is a block diagram for simply showing the position of the magnetic domain control layer in the yoke structure. In detail, the magnetic domain control layer is manufactured in a structure of the magnetoresistive sensor layer as one example of the present invention viewed from the media-opposed surface and a structure represented by the diagram showing a section of the depth direction, as shown in FIGS. 8 and 9.

FIG. 14 shows a schematic diagram of the flux guide type yoke structure and the magnetic domain control thereof. The surface viewed from the XY side in the diagram is the media-opposed surface. On the

5 magnetoresistive sensor layer disposed on the lower
shield 1002 so as to be recessed, is formed a soft
magnetic layer made of, for example, Ni₈₉Fe₁₉, as
indicated by 1401, having a shape, which extends from
the position exposed from the media-opposed surface
onto the magnetoresistive sensor layer, is in contact
with the surface opposite the media-opposed surface of
the magnetoresistive sensor layer, and extends to a
depth direction Z. This layer guides the magnetic flux
from the recording media to the magnetoresistive sensor
layer, and is called a flux guide. In order to magnetic
domain-control this flux guide layer, in the process of
forming the magnetoresistive sensor layer, ion milling,
patterning, forming the flux guide layer 1401, and
forming the magnetic domain control layer 1001, the
magnetic domain control material having high electric
resistivity of the present invention is used as the
magnetic domain control layer 1001 to give the
following advantages. Conventionally, the insulating
protective layer must be formed in the track width
direction of the magnetoresistive sensor layer. In the
present invention, even when the magnetic domain
control layer is formed directly, magnetic domain
control is possible without shunting. In the flux guide
type yoke structure, it is also possible to magnetic
domain-control the magnetoresistive sensor layer
together with the flux guide type yoke.

As shown in FIGS. 15 and 16, in order to increase

an amount of the magnetic flux sensed by the
magnetoresistive sensor layer, the portion in contact
with the magnetoresistive sensor layer of the yoke is
discontinuous. In such a structure, the material of the
5 magnetic domain control layer is a layer having high
electric resistivity so as to form the magnetic domain
control layer of the present invention. Examples of
arrangement of the magnetic domain control layer of the
yoke structure of this embodiment are shown in FIGS. 17
10 and 18.

(Example 6)

FIG. 19 is a diagram showing the magnetic disk
apparatus of one embodiment using the magnetic head
mounting the magnetoresistive sensor according to the
15 present invention.

The magnetic disk apparatus illustrated comprises
a magnetic disk 1901 as a magnetic recording media
formed in disk form for recording data in a recording
region called a concentric track and a magnetic
20 transducer, a magnetic head 1906 comprising a magnetic
transducer, reading and writing the data and mounting
the magnetoresistive sensor according to the present
invention (in detail, comprising a magnetic head 1910
and a slider 1909), actuator means 1911 for supporting
25 the magnetic head 1906 to move it to a predetermined
position on the magnetic disk 1901, and control means
for controlling transmission and receive of data by
read and written by the magnetic head and movement of

the actuator means.

The structure and operation will be described below. At least one rotatable magnetic disk 1901 is supported by a rotation axis 1902, and is rotated by the drive motor 1903. At least one slider 1909 is placed on the magnetic disk 1901, one or more sliders 1909 are disposed, and support the magnetic head 1910 according to the present invention for read and write.

The magnetic disk 1901 is rotated, and at the same time, the magnetic head 1906 is moved on the disk surface for access to a predetermined position in which data to be desired are recorded. The magnetic head 1906 is provided on an arm 1908 by a gimbal 1907. The gimbal 1907 has slight elasticity and brings the magnetic head 1906 into contact with the magnetic disk 1901. The arm 1908 is mounted on the actuator 1911.

There is a voice coil motor (hereinafter referred to as VCM) as the actuator 1911. VCM consists of a movable coil placed in the magnetic field fixed, and the movement direction and movement speed of the coil are controlled by an electric signal given from the control means 1912 through a line 1904. The actuator means of this embodiment comprises, for example, the magnetic head 1906, the gimbal 1907, the arm 1908, the actuator 1911 and the line 1904.

During operation of the magnetic disk, the magnetic disk 1101 is rotated to cause air bearing due to air flow between the magnetic head 1906 and the disk

surface, which lifts the magnetic head 1906 from the surface of the magnetic disk 1901. During operation of the magnetic disk apparatus, the air bearing is balanced with the slight elasticity of the gimbal 1907, the magnetic head 1906 is not in contact with the magnetic disk surface, and is maintained so as to be lifted from the magnetic disk 1901 at a constant interval.

The control means 1912 generally comprises a logic circuit, memory, and microprocessor. The control means 1912 transmits and receives a control signal through each line, and controls various structure means of the magnetic disk apparatus. For example, the motor 1903 is controlled by a motor driven signal transmitted through the line 1904.

The actuator 1911 is controlled so as to optimally move and position, by means of a head position control signal and a seek control signal through the line 1904, the magnetic head 1906 selected to a data track to be desired on the magnetic disk 1901 associated therewith.

The magnetic head 1910 reads data on the magnetic disk 1901 so as to convert the data to an electric signal. The control signal receives and decodes the electric signal through the line 1904. In addition, an electric signal written as data to the magnetic disk 1901 is transmitted through the line 1904 to the magnetic head 1910. In other words, the control means

1912 controls transmission and receive of information read or written by the magnetic head 1910.

The read and write signals described above permit means directly transmitted from the magnetic head 1910.

5 There are, for example, an access control signal and a clock signal as the control signal. The magnetic disk apparatus may have a plurality of magnetic disks and actuators, and the actuator may have a plurality of magnetic heads.

10 Such plurality of mechanisms are provided, so as to form the so-called disk array apparatus.

In this apparatus, the magnetoresistive sensor of the present invention is used as the magnetoresistive sensor of the magnetic head. It is thus possible to
15 improve reproducing resolution of the apparatus according to improved performance of the magnetoresistive sensor.

(Example 7)

FIG. 20 shows a representative structure of an
20 already known MRAM as one example of the magnetic recording sensor. The magnetic recording sensor has a structure comprising a plurality of cells in parallel including a magnetoresistive sensor layer 2002 for recording information, a bit line 2001 connected to the
25 magnetoresistive sensor layer for flowing an electric current to the sensor, a word line 2005 in the position opposite the bit line 2001 by interposing therebetween the magnetoresistive sensor layer 2002 and in the

position away from the magnetoresistive sensor layer
2002 for performing recording operation onto the
magnetoresistive sensor layer orthogonally to the bit
line, an amplifying system for amplifying a read signal,
5 and a read conductive line 2007 for switching between
read and write, wherein the magnetoresistive sensor
layer 2002 comprises the magnetoresistive sensor layer
as shown in Example 1. Since an electric current flows
perpendicular to the plane, the use of the
10 magnetoresistive sensor layer is similar to that of
Example 1. The magnetoresistive sensor layer has the
size consisting of one side of 0.2 to 0.25 μm . The
magnetization of the free layer of the magnetoresistive
sensor layer is rotated in the direction of an electric
15 current flowing through the word line and the bit line,
by varying the direction of the synthetic magnetic
field caused in the magnetoresistive sensor layer
portion. When the magnetization direction of the free
layer of the magnetoresistive sensor layer is rotated
20 and the magnetic domain is caused in the free layer,
the resistance value to the magnetic field is varied to
lower the S/N ratio, so that memory cannot be read. In
order to controllably perform this, the magnetic domain
control layer is required. Magnetic domain control
25 layers having high electric resistivity 2008 devised in
the present invention are positioned on opposite ends
of the magnetoresistive element layer 2002. Thus,
magnetic domain control is possible without loss of

shunting to the magnetic domain control layer, so as to improve the recording density of the magnetic recording sensor.

According to the present invention, in the
5 magnetoresistive sensor using the magnetoresistive
sensor layer, (1) a loss of shunting to the magnetic
domain control layer can be eliminated, (2) the number
of conventional processes for manufacturing the
magnetic domain control layer can be reduced, and (3)
10 magnetic domain control can be conducted finely by
making the gap between the shields smaller since the
thickness of the magnetic domain control layer can be
reduced by the size of the pressure-resistant
protective layer. Accordingly, (4) the magnetoresistive
15 sensor flowing an electric current perpendicular to the
plane can provide the magnetic domain control layer
practicable. Further, the magnetoresistive sensor of
the present invention is used to provide the magnetic
head having excellent reproducing resolution and the
20 magnetic disk apparatus.